

Green synthesis of Copper Nanoparticles using “Hemigraphis colorata” leaf extract and its characterization

Sorlin Selva Joice¹, Suprraja.S^{2*}, Karthikeyan.M³ S, Jeevanesh.E⁴, Mohamed Afsal⁵.

¹ Department of Pharmacognosy, Sri Ramakrishna Institute of Paramedical science, College of pharmacy, Affiliated to The Tamilnadu Dr.M.G.R.Medical University, Chennai, India.

^{2*,4,5} Department of Pharmacology, PSG College of Pharmacy, Affiliated to The Tamilnadu Dr.M.G.R.Medical University, Chennai, India.

³ Department of Pharmaceutical Analysis, PSG College of Pharmacy, Affiliated to The Tamilnad Dr.M.G.R.Medical University, Chennai, India.

Date of Submission: 05-05-2024

Date of Acceptance: 15-05-2024

ABSTRACT:

Purpose: To synthesize the copper nanoparticles Cu-Nps, and to find the antimicrobial activity of the plant “Hemigraphis colorata”.

Aim&objective: The aim of this research work was to synthesize g-Cu NPs mediated by Hemigraphis colorata medicinal plant leaf extract. The integration of bioactive compounds of this medicinal plant with Cu NPs is believed to be extremely beneficial for varieties of ailments. The biogenically synthesized g-Cu NPs were characterized using UV-visible, FT-IR, XRD, SEM, TEM and EDAX techniques. The antimicrobial properties of g-Cu NPs have also been evaluated against gram-positive and gram-negative bacteria.

Methodology: Hemigraphis colorata (or) murikooti is a prostrate herb with rooting branches, deep reddish leaves and white flowers. It belongs to the family Acanthaceae. The leaf was collected from the medicinal garden. Leaf was extracted for the synthesis of nanoparticles. The characterization of nanoparticles were noted (UV-vis, FT-IR, XRD, SEM, TEM, EDAX). The microbiological activity of the leaf is noted.

Results and discussion: The green synthesis Cu NPs were synthesized by using copper sulphate as a precursor and plant leaf extract as a reducing and capping agent. The change in color from blue to light brownish visually indicates the formation of copper NPs. The Cu NPs were washed by deionized water and ethanol to remove any unwanted particles.

KEYWORDS: Hemigraphis colorata, Green Synthesis, Cu NPs Characterization.

ranges between 1-100 nanometers in six undetectable by the human eye, nano particles can exhibit significantly different physical and chemical properties to their large materials counterparts. Copper nano particles is a copper based particle is 100nm size. copper nanoparticles with great catalytic activities can be applied to biosensors and electrochemical sensors. copper is one of the nine minerals that are recognized as essential nutrients for humans, as it plays an important role in different physiological normal processes in basically all human tissues, as well as skin. The plant Hemigraphis colorata is a versatile tropical low-creeping perennial herb. It is a prostrate growing plant with spreading rooting stems. The leaves are opposite, ovate to cordate, bearing well-defined veins, slender and lance shaped with toothed scalloped margins. The leaf has the chemical constituents such as sodium, calcium, Carboxylic acid, cinnamate, chlorogenate, coumarate, coumarins, flavonoid polyphenol, saponin, Tannin, ferulate, gallate, ascorbic acid, E-phenol, carbohydrates, steroids, saponins, tannins, proteins, flavonoids. Drug Delivery System is the controlled release of therapeutic agents. Drug Delivery System monitors the drug released and the location in the body where it is released. The upcoming drug delivery systems include the researches in the areas of crossing the Blood-Brain Barrier (BBB) in the brain, diseases and disorders, Enhancing targeted intracellular delivery, combining diagnosis and treatment. Drug delivery refers to approaches, formulations, technologies, and systems for transporting a pharmaceutical compound in the body some time based on nanoparticles [1] as needed to safely achieve its desired therapeutic effect. [2] It may

I. INTRODUCTION:

A nano-particles is a small particles that

involve scientific site-targeting within the body, or it might involve facilitating systemic pharmacokinetics; in any case, it is typically concerned with both quantity and duration of drug presence. Drug delivery is often approached via a drug's chemical formulation, but it may also involve medical devices or drug-device combination products. Drug delivery is a concept heavily integrated with dosage form and route of administration, the latter sometimes even being considered part of the definition. Nanoparticles can occur naturally or be created as the by-product of combustion reactions or be produced purposefully through engineering to perform a specialised function. Ability to generate the materials in a particular way the use of nanoparticles spans a wide variety of industries from healthcare and cosmetics to environmental preservation and air purification. In health care field nanoparticles e.g; utilises nanomaterials in a variety of ways, with one major use being drug delivery. A copper nanoparticle is a copper based particle is to 100nm size. A copper nanoparticles can be formed by material processes or through chemical synthesis. These nanoparticles are of particular interest due to their historical application as colouring agent and their modern biomedical ones. Copper nanoparticles are graded as highly flammable solids, they must be stored away from the ignition.

II. MATERIALS AND METHODS

Materials Collection:

The selected plant was collected from medicinal garden pallakad and authenticated at BSI, Southern Regional Centre its voucher no is **BSI/SRC/5/23/212**. The specimen was submitted for further references.

Methodology for Green Synthesis of Copper Nanoparticles

Plant leaves were collected and washed, the leaf powder was soaked 1 litre of distilled water and held in a shaker at 30 °C for 48 hours for continuous stirring at 50rpm for thorough mixing. The aqueous plant extract was used to reduce $\text{CuSO}_4 \cdot 5\text{H}_2\text{O}$, 100ml of plant extract was added into 90ml of 10mM of copper sulphate solution and kept in stirring for constant mixing under 50-60 °C temperature. A colour change of the solution was noted by visual examination, this confirmed the synthesis of copper nanoparticles. The characterization of nanoparticles were noted such as (UV-Vis, FT-IR, XRD, SEM, TEM, EDAX) The

anti-microbial property of copper nanoparticles was determined.

CHARACTERISATION TECHNIQUES:

UV-VISIBLE

An absorbance spectrum was recorded by allowing the instrument to scan wavelengths ranging between 200 and 800nm, and the absorbance of the nanoparticle solution against blank extract solution was collected.

FT-IR

Fourier transform-infrared spectroscopy (FT-IR) spectrum (FT-IR PerkinElmer) was recorded using KBr pellets in the range of 400-4000 cm^{-1} .

XRD

X-ray diffraction (XRD-Shimadzu X-ray diffractometer) (PXRD-7000) analytical technique was used to reveal crystalline nature of g-Cu NPs.

SEM

The scanning electron microscopy with energy-dispersive X-ray spectroscopy (SEM-EDX-EVO18 model with low vacuum facility and ALTO 1000 Cryo attachment).

TEM

Transmission electron microscope high-resolution (JEM-2100plus HRTEM) were used for understanding morphological and structural features of g-Cu NPs.

III. RESULTS AND DISCUSSION:

The green synthesis Cu NPs were synthesised by using copper sulphate as a precursor and plant leaf extract as a reducing and capping agent. The change in colour from blue to light brownish visually indicates the formation of copper NPs. The Cu NPs were washed by deionised water and ethanol to remove any unwanted particles.

Characterisation of green synthesised copper nanoparticles

UV - Vis spectroscopic analysis of copper nanoparticles :

UV spectroscopy within the 200-800 nm range initially verified the development of CuNPs. A characteristic peak of 575 nm showed the absorption spectrum of green synthesised CuNPs.

FT-IR Spectral Analysis:

A Fourier transform infrared spectroscopy was utilised as an affirmative method for the construction of nanoparticles. This study offers an

imprint of current molecules vibrational and rotational modes, thus helping to classify the functional and potential plant molecules involved in copper nanoparticles reduction (Fig.1)




Fig 1: FT-IR Analysis of Copper Nano Particles

XRD Analysis:

The structure of the nanoparticles indicated by XRD analysis of the synthesised

copper nanoparticles. At 2θ values of 44.32° , and 65.25° degrees, diffraction peaks observed. (Fig 2)




Fig.2: XRD Analysis of Copper Nano Particles

Morphological Analysis by SEM:

FE-SEM analysis used to study the shape and size of the copper nanoparticles. The SEM study carried out using the Schottky FE-SEM (Japan) TESCAN MIRA3 LMH model.

Microscopy of copper nanoparticles has shown that they have a nano-range particle size (500nm) which is spherical and homogeneous in distribution. Under the FE-SEM Microscope. (Fig.3)




Fig.3: FE-SEM observation of green synthesised copper nanoparticles

Morphological and Compositional Analysis by TEM and EDAX:

To get the further deep insight on the morphology, size, and crystalline nature of the copper nanoparticles TEM analysis was employed.

The TEM images of green synthesised copper nanoparticles (Figure 4) shows that the synthesised nanoparticles exhibited different shapes. Plant extract as capping and stabilising agents. (Fig.4)




Fig 4: TEM images of green synthesised copper nanoparticles at lower magnification (100nm) and

higher magnification (20 nm).

EDAX analysis

The elemental analysis of the copper nanoparticles forms the EDAX spectrum of the FE-SEM. The EDAX spectrum is consistent with the

presence of copper in the nanoparticle. The percentage of molecular mass and atomic values of Cu is 32% and 8.31 % respectively.(Fig 5)




Fig 5: EDAX analysis of green synthesised copper nanoparticles

Table No 1: Chemical composition of nano-particles using EDAX analysis

Element	Line Type	k Factor	k Factor type	Absorption Correction	Wt%	Wt% Sigma	Atomic %
C	K series	2.769		1.00	63.94	0.51	87.81
O	K series	2.020		1.00	3.40	0.22	3.50
Si	K series	1.000		1.00	0.64	0.08	0.37
Cu	K series	1.247		1.00	32.02	0.47	8.31
Total:					100.00		100.00

Antimicrobial activity

Testing the susceptibility of antimicrobial agents can be done in a flexible way using the disc diffusion method. It is frequently employed in

research on the antibacterial properties of plant extracts and naturally occurring antimicrobial agents.

Table No 2: Antimicrobial activity

S.NO	Test organism	Zone of Inhibition (mm) n=2	
		Staphylococcus aureus	Escherichia coli
1	Copper nanoparticles	11	15
2	Clotrimazole (30µg)	13	30

Antibacterial Activity

Antibacterial activity is a substance's ability to kill bacteria or slow their growth. Antibacterial

chemicals can kill bacteria on a local level while remaining non-toxic to surrounding tissue.



S. A (Staphylococcus aureus)



E. coli (Escherichia coli)

Fig 6: Antibacterial activity

IV. CONCLUSION

The green copper nanoparticles (g-Cu NPs) were successfully synthesized by using medicinal plant *Hemigraphis colorata*. The biogenically synthesized g-Cu NPs were characterized using UV-visible, FT-IR, XRD, SEM, TEM and EDAX techniques. The present research work gives comprehensive report on synthesis and antimicrobial activities of g-Cu NPs which in turn will have significant impact on biomedical applications. The UV-visible absorbance and reflectance spectra showing λ_{max} of 575 nm. FTIR spectra supported the presence of capping agents on the surface of g-Cu NPs. The crystalline nature and composition of g-Cu NPs were confirmed by XRD pattern and EDAX spectrum, respectively. The SEM and TEM micrographs provided enough evidence towards the nano morphology of g-Cu NPs with Spherical shapes with an average particle size of 500nm and Homogenous distribution. The antimicrobial properties of g-Cu NPs have also been evaluated against gram-positive and gram-negative bacteria. The g-Cu NPs synthesized by using the leaf extract of *Hemigraphis colorata* against pathogens *Staphylococcus aureus*, *Escherichia coli* showed a broad range of antibacterial activity with a zone of inhibition 11 and 15 mm respectively. The wide zone of inhibitions of g-Cu NPs against pathogens confirms their great potential as a

remedy for infectious diseases caused by the tested bacterial pathogens.

REFERENCE

- [1]. J Saravanan, NH Joshi, VG Joshi, PS Sutar, AA Kariga "Woundhealing activity of *Hemigraphis colorata* " Int J Contemp Res Rev, 1 (5) (2010), pp. 1-3
- [2]. VP Silja, K Samitha Varma, KV Mohanan "Ethnomedicinal plant knowledge of the Mullukuruma tribe of Wayanad district, Kerala" Indian J Tradit Knowledge, 7 (4) (2008), pp. 601- 612
- [3]. R Jasmine, P Daisy, BN Selvakumar "Evaluating the antibacterial activity of *Elephantopus scaber* extracts on clinical isolates of β -lactamase producing methicillin resistant *Staphylococcus aureus* from UTI patients" Int J Pharmacol, 3 (2) (2007), pp. 165-169
- [4]. Shenmar, R., Norsten, V.B., Rotello, V.M.: Polymer-mediated nanoparticle assembly: structural control and applications. Adv. Mater. 6, 657-669 (2005)
- [5]. Balzani, V., Credi, A., Venturi, M.: The bottom-up approach to molecular-level devices and machines. Chem. A

- Eur. J. 24, 5524–5532 (2002)
- [6]. Lambert, S., Cellier, C., Gaigneaux, E.M., Pirard, J.P., Heinrichs, B.: Ag/SiO₂, Cu/SiO₂ and Pd/SiO₂ cogelled xerogel catalysts for benzene combustion: relationships between operating synthesis variables and catalytic activity. *Catal. Commun.* 8, 1244–1248 (2007)
- [7]. Zhang, H., Zhu, Q., Zhang, Y., Wang, Y., Zhao, L., Yu, B.: One-pot synthesis and hierarchical assembly of hollow Cu₂O microspheres with nanocrystal-composed porous multishell and their gas-sensing properties. *Adv. Funct. Mater.* 17, 2766–2771 (2007)
- [8]. Liu, Z., Bando, Y.: A novel method for preparing copper nanorods and nanowires. *Adv. Mater.* 15, 303–305 (2003)
- [9]. Oritz, J.R., Ogura, T., Medina-Valtierra, J., Acosta-Ortiz, S.E., Bosh, P., De las Reyes, J.A., Lara, V.H.: A catalytic application of Cu₂O and CuO films deposited over fiberglass. *Appl. Surf. Sci.* 174, 177–184 (2001)
- [10]. Jayaprakasan, M.V., Viswanathan, K., Rajesh, M. and Pradyumn, P.P., 2014. Ayurvedic preparation from *Azadirachta indica*, *Terminalia chebula*, *Hemigraphis colorata* extracts and its antimicrobial investigation. *IOSR Journal of Pharmacy and Biological Sciences*, 9(2), pp.01-06.
- [11]. Korkina, L.G., Mikhal'Chik, E., Suprun, M.V., Pastore, S. and Dal Toso, R., 2007. Molecular mechanisms underlying wound healing and anti-inflammatory properties of naturally occurring biotechnologically produced phenyl propanoid glycosides. *Cell Mol Biol*, 53(5), pp.84-91.
- [12]. Kulkarni, Y.A. and Veeranjanyulu, A., 2013. Effects of *Gmelina arborea* extract on experimentally induced diabetes. *Asian Pacific journal of Tropical Medicine*, 6(8), pp.602-608.40
- [13]. Kumar, B., Vijayakumar, M., Govindarajan, R. and Pushpangadan, P., 2007. Ethnopharmacological approaches to wound healing—exploring medicinal plants of India. *Journal of Ethnopharmacology*, 114(2), pp.103-113.
- [14]. Murugesan, D. and Deviponnuswamy, R., 2014. Potential anti-inflammatory medicinal plants—a review. *Int J Pharm Pharm Sci*, 6(4), pp.43-49 Palladino MA, Bahjat FR, Theodorakis
- [15]. Arivazhagan S, Balasenthi S and Nagini S (2000). Antioxidant and anti-inflammatory activities of *Mallotus oppositifolium*. *Journal of Phytotherapy Research* 14 (4) 291-293.
- [16]. Bhargavi CHS, Kumar ADA, Kumar NVSPP, Babu VR. (2011) Ancient and Modern View of Wound Healing: Therapeutic Treatments. *RJPBCS*;2:474-479.
- [17]. Bourdy G, Walter A. (1992) Maternity and medicinal plants in Vanuatu I. The cycle of reproduction. *J Ethnopharmacol*; 37:179-196.
- [18]. Chang C, Yang M, Wen H, Chem J (2002) Estimation of total flavonoid content in propolis by two complementary colorimetric methods. *J. Food Drug Anal.* 10:178-182
- [19]. Chia-Jung Lee, Lih-Geeng Chen, Wen-Li Liang, Ching-Chiung Wang (2010) Anti-inflammatory effects of *Punica granatum* Linne in vitro and in vivo. *Food Chemistry* 118, 315–322.
- [20]. Deepak RP, Renjima V, Murugan K. (2007) Antioxidant Potential of *Hemigraphis colorata* (Blume) H.G. Hallier and *Rhinacanthus nasutus* (Linn). Kurz. – A Search. In Proceedings of the 2007 Kerala Science Congress (03-40), Kannur, Kerala, 1-4.